

Duolam



The following certificates demonstrate the outstanding quality of our products:



Type of wood	spruce/fir
Standard and strength	GL 24h according to EN 14080:2013
Gluing	according to EN 14080:2013 and EN 302/301 melamine/urea resin, Type 1, 90°C-B Service class 1, 2 and 3* as per EN 1995-1-1
Dimensions	Width: 80–240 mm Height: 60 mm und 80 mm Length: 12 m and 13 m
Surface and tolerance of dimension	planed on 4 sides with chamfer ± 1 mm in width and height ± 3 mm length tolerance
Wood moisture	12 % ± 2 %

*up to cross section of 60,000 mm², protective coating required if close to the sea

Mechanical properties



Strength class	GL 24h	
Elasticity modulus	$E_{//\text{mean}}$	11.500 N/mm ²
	$E_{\perp\text{mean}}$	300 N/mm ²
Shear modulus	G_{mean}	650 N/mm ²
Bending strength	$\sigma_{0,05}$	24 N/mm ²
Tensile strength	$\sigma_{t//0,05}$	19,2 N/mm ²
	$\sigma_{t\perp0,05}$	0,5 N/mm ²
Compressive strength	$\sigma_{c//0,05}$	24 N/mm ²
	$\sigma_{c\perp0,05}$	2,5 N/mm ²

Features	Permissibility
Glued joint	open joint permissible up to a depth of 1/6 of the component width per side
Fracture in wood	not permissible
Rough areas	recessed rough areas occasionally permissible
Discoloration/red stripes	permissible
Resin pockets	permissible
Bark inclusions	permissible up to max. 1/2 board width
Chunking	permissible
Sound knots	permissible
Loose knots	permissible

Features	Permissibility
Tiny knots	permissible
Solid dead knots	permissible
Heartwood	permissible
Insect attack	small wormholes up to 2 mm permissible
Waney edge	turned inwards max. 2 cm measured obliquely permissible
Rot areas	not permissible
Checks	permissible
Packaging and storage	Wrapped with PE film in packages. Store dry in a hall or under a roof. Protect from sunlight.

Standard dimensions strength class GL 24h Amount per packet

Width in mm	Height in mm	
	60	80
80	91	75
100	77	60
120	63	50
140	56	40
160	49	35
180	42	30
200	35	30
220	35	25
240	28	25

 Stock program in lengths 12 m or 13 m
 Standard dimensions

Imprint

Mosser Leimholz Gesellschaft m. b. H.

Company headquarters & postal address:

Fohlenhof 2
A-3263 Randegg
+43 7487 62 71-0
office@mosser.at

Register court: District Court of St. Pölten

Commercial register number: FN93662p

Sales tax ID number: ATU20146606

Chamber affiliation: Member of the Austrian Wood Industries Association

Legal notice:

The information on the Internet regarding the Mosser Group is continuously checked and updated. Nevertheless, incorrect information may be included unintentionally.

Therefore, liability or a guarantee for the topicality, correctness and completeness of the information provided cannot be assumed.

All decisions which are based on the information contained on the Internet concerning the Mosser Group are solely the responsibility of the user.

The Mosser Group does not accept any liability for direct, concrete or any other damage which arises as a result of this information.

The content and structure of the Mosser website are copyrighted. Duplication of information or data, particularly the use of text, sections of text or images, requires permission from the Mosser Group.

Form number: QM_QB_0040

Version number: .07

Description: Produktdatenblatt Duolam_ENG

Creator: Daniela Heigl

Approver: Reinhard V. Mosser

Release date: 01.09.2020